



PAIRUI



Http: fuantronics.com

P3 **T6*3*2** **HP**
Material **Core Size** **Coating**
 材质 品名 涂装

HP: Parylene Coating of Ja; pgem-Free

Dimensions: (UNIT:mm)


Dimensions(mm)			
Parylene Coating Dimensions(mm)			
ΦD1	ΦD2	H	Wt(g/set)
6.0±0.3	3.0±0.3	2.0±0.2	0.21
6.0±0.3	3.0±0.3	2.0±0.2	



Ferrite core

Test Conditions

AL: F=10.0KHz U=0.3V N=10Ts



Effective parameter

	Ve(mm3)	Ae(mm2)	Le(mm)
	42.4	3.0	14.1

Coating


The core are coated with epoxy, flame retardant in accordance with "UL 94V-0" file number E228348. The colour is green.

Ring core data


GRADE	AL(nH)	μi	TYPE NUMBER
P3	660±25%	≈2300	T6/3/2/P3
H5K	1400±25%	≈5000	T6/3/2/H5K
H7K	1950±25%	≈7000	T6/3/2/H7K
H10K	2800±30%	≈10000	T6/3/2/H10K

Note:


- 1: Document is the property of FUAN Inc & is not allowed to be duplicated without authorization
- 2: RoHS compliant.




P3



H5K



H7K



H10K